Anti-Ermüdungsmatte Sky 2-lagig für industrielle Anwendungen







- Ergonomic benefit of 19 mm thickness worker platform deriving from a long wearing bubble design top PVC surface (5 mm) laminated on to a resilient microcellular vinyl base (14 mm).
- Floormatting products, • Similar to other SkyTrax[™] is a very strong and durable product giving extra comfort and fatigue relief to workers while enhancing traction.
- Any length available, factory finished and overnight delivery.
- Uni-Fusion™ lamination technology, engineered to resist in the harshest work environments.
- RedStop™ technology, engineered to increase friction with smooth floor surfaces anchoring the mat in place.
- Resistant to most industrial fluids and chemicals.
- Slip resistance according to DIN51130 and BG-rule BGR181.
- All 4 sides are bevelled to minimize tripping.
- Available with yellow borders along sides comply with OSHA code 1910-144.
- Free of toxic DOP and DMF.



	P	RODUCT SPECIFICATIONS	
Designation	Industrial matting		
Туре	Anti-fatigue		
Description	Laminated with bubble top surface		
Material	PVC on microcellular vinyl base		
Process	Laminated, Uni-Fusion™ technology		
Category	Best		
Recommended use	Heavy duty – dry industrial environments		
Colours	Grey, Black, Black/Yellow		
Weight	6,3 kg/m ²		
Thickness	19 mm		
Standard sizes	60 cm x 91 cm 91 cm x 152 cm 91 cm x 200 cm 60 cm x 21,9 m 91 cm x 21,9 m 122 cm x 21,9 m 152 cm x 21,9 m		
Custom sizes	60 cm, 91 cm, 122 cm and 152 cm per linear meter		
Special remarks	Any length available, factory finished and shipped overnight.		
1		PRODUCT TESTING	
	Tests	Norms	Results
Compression deflection		U.S.	
	1.4 kg/cm ²		0,52 cm
	2.8 kg/cm ²		0,82 cm
Foam battery		ASTM D3574	40 lb/in ²
Taber abrasion resistance		ASTM D3884-01	
	1000 gr - 500 Revs		0,1% weight loss
Static coefficient of friction		ASTM C1028-96	0,82
Elongation		ASTM D412	150%
Breaking load		ASTM D412	1000 lb/in ²
Graves tear strength		ASTM D1004	65,7 lbs
Hardness		ASTM D2240-02	95 Shore A
Aging & weathering		ASTM D750	No visual change
Ozone exposure		ASTM D518	No change
Anti-slip		DIN51130 and BG-RULE BGR181	R9
		FIRE TESTING	
	Critical radiant flux	ASTM E-648	
	Fine notendary and	DIN4102	
	Fire retardancy	EN 13501-1	CFL-S2
	Flammability test	ASTM-D2859	Pass
ESD		ANSI ESD S7.1 50% Humidity	
Sustainability		 Recyclable material Reach Compliant (Registration, Evaluation, Authorization and Restriction of Chemicals) 	